Jai Kamal Paints

MANUFACTURERS OF PAINTS & VARNISH

EPIJAY

ZINC PHOSPHATE PRIMER GREY / REDOXIDE

DESCRIPTION: A two pack polyamide cured epoxy anticorrosive primer with

zinc phosphate pigment. The red version contains red oxide in addition to zinc phosphate. The primer gives excellent adhesion to steel and offers efficient protection against chemicals and corrosion. Mainly used in maintenance of pulp and paper mills, refineries, petrochemicals, ore handling, metal and engineering industries. It is compatible with a wide range of epoxy,

chlorinated and polyurethane top coats.

TYPE : Two Pack; Cold Cured

COMPOSITION: Epoxy resin pigmented with zinc phosphate / redoxide

COLOUR : Grey / Red

MIXING RATIO : Base: Adduct; 3:1 by volume

POT LIFE : 4-8 hrs.

APPLICATION : Airless / Conventional Spray / Brush

THEORETICAL : 9 Sqmt.@ 50 Microns COVERAGE 17 Sqmt. @ 25 Microns

RECOMMENDED DFT: 25 - 50 Microns

DRYING TIME : Touch Dry - 2 to 3 hrs.

OVERCOATING: Minimum: 18 hrs. **INTERVAL** Maximum: 7 days

CURING TIME : 6 - 7 Days

FLASH POINT : Above 20 °C

THINNER: 'Epijay' Epoxy Thinner.



Jai Kamal Paints

MANUFACTURERS OF PAINTS & VARNISH

FINISH : Matt

RESISTANCE

TEMPERATURE : 120 °C dry heat

STORAGE: Upto 12 months. Materials to be kept in original sealed container

in dry place.

OVERCOAT: Epoxy, Chlorub and polyurethane finishes.

SURFACE OF : Degrease and blast clean to SA 2½ grade minimum. If blast cleaning is not practical, then mechanical cleaning by use of

tools along with manual chipping and wire brushing should be

done. The surface should be clean and dry.

METHOD OF: Base to be thoroughly mixed. Then 3 parts of base and 1 part of adduct by volume to be mixed thoroughly for consistency.

adduct by volume to be mixed thoroughly for consistency. Maturation time of 30 minutes to be allowed. The mixture to be

stirred well before and during use.

(THE INFORMATION IN THIS LEAFLET IS GIVEN IN GOOD FAITH, BUT WITHOUT WARRANTY)

Jai Kamal Paints