



MEMBER
THE INDIAN PAINT ASSOCIATION



Jai Kamal Paints

MANUFACTURERS OF PAINTS & VARNISH

JAICHLOR

RED OXIDE ZINC CHROMATE PRIMER

DESCRIPTION	:	A chlorinated rubber base primer – it provides to give excellent resistance of chemical environments when coated with chlorub based finish paints. Ideal for corrosive and marine environments; gives excellent resistance to fresh and salt water spray when applied in system.
TYPE	:	Single pack; Air Drying
COMPOSITION	:	Plasticised chlorinated rubber medium pigmented with anti-corrosive pigments – red oxide and zinc chrome.
COLOUR	:	Red Oxide
APPLICATION	:	Brush / Airless Spray
THEORETICAL COVERAGE	:	8 Sqmts. Per ltr.
RECOMMENDED DFT	:	35-50 Microns per coat
DRYING TIME	:	Touch Dry -- 30 minutes
OVER COATING INTERVAL	:	Minimum 8 hrs. Maximum 12 hrs.
FLASH POINT	:	Above 25 °C
THINNER RECOMMENDED	:	'JAICHLOR' Chlorinated Thinner
FINISH	:	Matt
TEMPERATURE RESISTANCE	:	65 °C Dry Heat

'THE DECORATIVE PROTECTION THAT STANDS THE TEST OF TIME'

(Old No.70) New No 169 MS KOIL STREET, ROYAPURAM, CHENNAI-600 013, Ph 2598 1323 2595 6660



MEMBER
THE INDIAN PAINT ASSOCIATION



Jai Kamal Paints

MANUFACTURERS OF PAINTS & VARNISH

- STORAGE** : upto 12 months. Material to be kept in original sealed container in dry place under normal temperature conditions.
- OVERCOAT** : Chlorinated Rubber based paint '*Jaichlor*' chlorinated rubber MIO paint
- NOTES ON SURFACE PREPARATION** : Sand blast to SA 2½ grade. If sand blasting is not practicable mechanical cleaning to St – 2 std. Should be done.
- METHOD OF APPLICATION** : Stir well before use. Application by brush or airless spray.
- LIMITATION** : Not recommended against petroleum solvent spillage.

(THE INFORMATION IN THIS LEAFLET IS GIVEN IN GOOD FAITH, BUT WITHOUT WARRANTY)

Jai Kamal Paints

'THE DECORATIVE PROTECTION THAT STANDS THE TEST OF TIME'

(Old No.70) New No 169 MS KOIL STREET, ROYAPURAM, CHENNAI-600 013, Ph 2598 1323 2595 6660